

PU STRUCTURAL FOAM

H200-AT

POLYURETHANE FOAM

01/18
June 2018

CHARACTERISTIC

H200-AT is a closed cell, 2 component hard foam that cures to a non porous surface when poured into a mould. The foam has a cup density of approx. 200 kg/m³ and good mechanical strength. Due to its long reaction time it can be mixed and poured by hand easily. Mechanical stirring reduces the density and start time. A large amount poured into a closed mould increases the density and the pressure exerted against the mould. H200-AT is used with the B component Type II and is resistant to diluted acids, bases and water.

AREA OF APPLICATION

Mechanically shapeable components with a non porous surface:

- Orthopaedic components
- Lids
- Doors
- Arm chair shells
- Casing for apparatus

PRODUCT DATA

Material data of the liquid product		
Colour	Component A yellowish	Component B brownish
Density at 20 °C	approx. 1.09 g/cm ³	approx. 1.22 g/cm ³
Viscosity at 20 °C	approx. 2600 mPa.s	approx. 300 mPa.s
Material data of the mixture at 20°C		
Mixing ratio A : B	100 : 100 pbw (parts by weight) 100 : 89 pbv (parts by volume)	
Start time	approx. 65 seconds	
Setting time	approx. 130 seconds	
Rise time	approx. 180 seconds	
Material data of the cured product		
Density	approx. 200 kg/m ³ (free-rise foamed)	
Expansion	approx. 1 : 5	
Storage (at room temperature and dry)	minimum 6 month in the closed original container	

VOSSCHEMIE GMBH

Esinger Steinweg 50
25436 Uetersen
Germany
www.vosschemie.de

SITZ DER GESELLSCHAFT
Uetersen

AMTSGERICHT
Pinneberg – HRB 0265 EL
USt-Id-Nr.: DE134800975
ILN: 41 02870 00000 8

GESCHÄFTSFÜHRER
Dieter Voss, Klaus Voss,
Hans-Joachim Rohde

NIEDERLASSUNGEN
Ratingen, Oschatz, Kolbermoor

Qualitätsmanagement-System
zertifiziert von LLOYD'S nach
der Qualitätssicherungsnorm
DIN EN ISO 9001 : 2015



:: INSTRUCTION FOR USE

The volume of the cavity which is to be filled has to be approximately calculated. In order to ensure a continuous, high foam quality, it is necessary to maintain the following conditions:

- 1) Stir the A-component thoroughly before use.
- 2) Ensure that both components are kept at a minimum constant temperature of 18°C.

Weigh out both components using the stated mixing ratio and mix both thoroughly. When mixing large amounts use a mixing propeller on a drill with a speed of 1500 rpm to ensure thorough and rapid mixing. The foam is then poured into the cavity. When more than the calculated amount of foam is poured into the mould or cavity the pressure on the walls increases as does the specific gravity. This must be taken into account.

Long moulds must not be placed horizontally but at an angle of 10° to 15°. Inject the foam at the lowest point of the mould, making sure there is provision for air vents at the top of the mould. The surface temperature of the cavity or mould should be between 15°C and 25°C. Two component foams can also be applied by machine.

:: SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Security Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry .

Copyright VOSSCHEMIE