Carbon fabric 160 g/m² (twill weave)

Technical Data Sheet



Item no.	CT-160125T
Description	CARBON-fabric_ 3K Carbon 160 g/m² (twill weave), 125 cm

Layer	Construction
Warp (thr./cm)	**4.0** - 200 tex 3K carbon fibre
Weft (thr./cm)	**4.0** - 200 tex 3K carbon fibre

Fibre properties

Yarn	Carbon 3K
Tensile strength	4000 MPA
Tensile modulus	230 GPA
Elongation at break	1.7 %
Resin compatibility	Polyester, Vinylester, epoxy resins
Test method	ISO 10618

Storage	Store in a cool, dry place and protect from direct sunlight.

Edition 06/2025, subject to change

All information, recommendations, and advice on the part of R&G Faserverbundwerkstoffe GmbH are published to the best of our knowledge and belief. They are noncommittal and contain neither explicit nor tacit assurance or warranty of particular properties. The values specified for properties are typical figures. Recommendations or advice serve to describe our products and possible applications in a general or exemplary, but not specifically individual manner. In the course of the constant technical advancement and improvement of our products there may be changes to the characteristic values, copy, and diagrams; no specific reference is made to any such change. Owing to our products' wide and highly diverse range of potential applications far beyond any of our attempts to analyse, the customer alone is responsible for examining our products' suitability for the respective processes and purposes and their respective processibility. All and any protective rights and the applicable laws, terms, and conditions must be observed by the buyer or user of our products at their own responsibility. Publication is not a licence and does not intend the violation of any patents.