

vDijk Pultrusion Products  
ASTM D3039 Tensile Polymer Matrix  
Tinius Olsen 50ST  
Epsilon 3542 Extensometer

Date: 07-05-2020  
Batch No.: Vooraad  
Product Code: H1RE3B00 (Example)  
Speed: 2,00 mm/min

Specimen	Width mm	Thickness mm	Ultimate Force kN	Tensile Strength MPa	Modulus GPa	Strain %	Remarks
1	2,88	0,60	4,24	2.456	274	0,88	
Average	2,88	0,60	4,24	2.456	274		
SD	N/A	N/A	N/A	N/A	N/A		

