

vDijk Pultrusion Products
 ASTM D3039 Tensile Polymer Matrix
 Tinius Olsen 50ST
 Epsilon 3542 Extensometer

Date: 22-01-2019
 Batch No.: 190118D
 Product Code: C1R01A00 (R&G Order no. 60010000-100)
 Speed: 2,00 mm/min

Specimen No.	Diameter mm	Ultimate Force kN	Tensile Strength MPa	Modulus GPa	Ultimate Strain %	Remarks
1	0,970	2,454	3321	146	2,31	
2	0,970	2,301	3114	146	2,61	
3	0,970	2,443	3306	139	2,32	
4	0,970	2,347	3175	143	2,17	
5	0,970	2,294	3104	145	2,18	
Average	0,970	2,368	3204	144		
SD	0,00	0,07667	103,8	2,85		

