

TECHNICAL DATASHEET



Article: Style 442
Setting (Thr/cm): 4,0/4,0
Weave: Twill 2/2
Finish: one side coated

<u>Construction:</u>	Warp	Weft
Yarn material ¹⁾ :	Carbon 3K	Carbon 3K
Yarn number ¹⁾ :	200 tex	200 tex

<u>Technical Data:</u>		Unit	Target	+/-	Tolerance
Fibre density ^{1) 3)}	Warp	g/cm ³	n.G.	+/-	n.G.
	Weft	g/cm ³	n.G.	+/-	n.G.
Linear density ¹⁾	Warp	tex	200	+/-	10
	Weft	tex	200	+/-	10
Twist ¹⁾	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	Thr./cm	4,0	+/-	0,2
	Weft	Thr./cm	4,0	+/-	0,2
Weave			Twill 2/2		
Weight		g/m ²	173	+/-	12
Dry weight		g/m ²		+/-	
Moisture content		%		+/-	max.
Thickness ²⁾		mm		+/-	
Width		cm	as ordered	+/-	1

¹⁾ = n.G. = depending on order and yarn specification

³⁾ = no measure, certified by supplier

²⁾ = approximate value, not for release

<p>Remarks:</p> <p>with ep-binder 10-15 g/m²</p>
--

<p>Date</p> <p>19.08.2010</p>	<p>Q.A.</p> <p>Monika Dassel</p>	<p>This Datasheet does not include Revision Service.</p>
--------------------------------------	---	---