



## Technical Data

### Glass non-crimp fabric 440 g/m<sup>2</sup> (biaxial, silane)

Technical Characteristics				
	Unit	Nominal Value	Test Method	
Glass Composition	E glass			
Weight per unit area	g/m <sup>2</sup>	440	ISO 3374	
Deviation from the nominal value	%	± 5		
1st layer :	-45°	g/m <sup>2</sup>	217	300 Tex
2nd layer :	0°	g/m <sup>2</sup>	3	68 Tex
3rd layer :	90°	g/m <sup>2</sup>	4	68 Tex
4th layer :	+45°	g/m <sup>2</sup>	217	300 Tex
Sewing thread polyester bonding	g/m <sup>2</sup>	≤10 Stitching		
Width	cm	127		ISO 5025
Deviation from the nominal value	%	± 1.9		

All information, recommendations, and advice on the part of R&G Faserverbundwerkstoffe GmbH are published to the best of our knowledge and belief. They are noncommittal and contain neither explicit nor tacit assurance or warranty of particular properties. The values specified for properties are typical figures. Recommendations or advice serve to describe our products and possible applications in a general or exemplary, but not specifically individual manner. In the course of the constant technical advancement and improvement of our products there may be changes to the characteristic values, copy, and diagrams; no specific reference is made to any such change. Owing to our products' wide and highly diverse range of potential applications far beyond any of our attempts to analyse, the customer alone is responsible for examining our products' suitability for the respective processes and purposes and their respective processibility. All and any protective rights and the applicable laws, terms, and conditions must be observed by the buyer or user of our products at their own responsibility. Publication is not a licence and does not intend the violation of any patents.