

GLASS FILAMENT FABRICS for PLASTICS REINFORCEMENT
PRODUCT SPECIFICATION

			Specification
Style Number	04367	Old ITG desc.	04367 MIL-Y-1140H
US Style			AMS / MIL-C-9084
WLB No.			DIN 65066
British Standard			BS 3396

Finish/Designatio	FK144
--------------------------	-------

	Unit	Tolerance		Specification
Weave pattern		HD-Weave		DIN ISO 9354
Area weight	g / m ²	600,0	± 5%	DIN EN 12127
Yarn	tex			DIN EN 12654
warp yarn		EC9-68 tex		
weft yarn		EC9-272 tex		
Fibre count	1 / cm			DIN EN 1049
warp ends		44,0	± 5%	
weft picks		11,0	± 5%	

Temperature resistance 1)				
Continuous load	°C	260		
Short time resistance	°C	600		

Moisture content	%	< 0,2		DIN EN 3616
Finish content	%	0,08 - 0,28		DIN ISO 1887
				DIN EN 60

Thickness (approx. dry)	mm	0,75	± 5%	DIN ISO 4603/E
in laminate (43% Vol.)	mm	0,54	± 5%	

All statements herein are expressions of opinion which we believe to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, express or implied, is made or intended.
Porcher Industries Germany GmbH, Benzstraße 14, D-89155 Erbach, Telefon +49 (0)7305 / 955-485, Fax +49 (0)7305 / 955-524

GLASS FILAMENT FABRICS for PLASTICS REINFORCEMENT
PRODUCT SPECIFICATION

	Unit	Standard	P-D ITG	Tolerance	Specification
Style Number		04367		/ FK144	
Tensile Strength					ASTM D 4029
warp	N/cm			>	
weft	N/cm			>	
Tensile strength					DIN EN 2747
warp	MPa	370		>	
weft	MPa	370		>	
Young's-Modulus					
warp	GPa	19		>	
weft	GPa	19		>	
Compression strength					DIN 53454
warp	MPa	370		>	DIN 65380
weft	MPa			>	DIN prEN 2580
Compression-Modulus					
warp	GPa			>	
weft	GPa			>	
Interlaminar shear strength					DIN EN 2377
warp	MPa			>	
weft	MPa			>	
Flexural strength					DIN EN 2746
warp	MPa			>	
weft	MPa			>	
Flexural-Modulus					
warp	GPa			>	
weft	GPa			>	

All statements herein are expressions of opinion which we believe to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, express or implied, is made or intended.
Porcher Industries Germany GmbH, Benzstraße 14, D-89155 Erbach, Telefon +49 (0)7305 / 955-485, Fax +49 (0)7305 / 955-524

Remarks

1) Temperature resistance for dry fabrics